

## Lubricant Product Information



# Daphne Oil Coat RL 55

High Performance Anti Rust Oil

### Description

Daphne Oil Coat RL 55 is a low viscosity rust preventive oil formulated with highly refined light mineral base oil incorporating special anti-rust additives and oil film protection agent to provide excellent rust preventive performance.

### Application

Recommended as a rust preventive oil for bolts & nuts, wire, steel plate and steel pipe. It is suitable for use in both in-process storage and during shipping period. Its low viscosity makes it most suitable for cleaning/ rinsing use.

#### Rust Preventive Period

In-door without wrapping: Above 1 month  
In-door with wrapping: Above 3 months

#### Rust Characteristics

Shed Storage Expose Test 2 Mths A class  
Humidity Cabinet Test 240 Hrs A class  
Indoor Exposure Test 1 Mths A class  
Salt Spray Test 24 Hrs A class

### Characteristics

1. Excellent anti-rust properties in spite of low viscosity.
2. Excellent cleaning/ rinsing properties due to its low viscosity.
3. Easily removed with hydrocarbon and water soluble cleaners.
4. Economical to use due to low oil consumption.

### Packing

20L pail, 200L drum

The information provided is to our best knowledge, true & accurate, subjected to change without notification due to continual product research and development. All recommendations or suggestions are without guarantee since the conditions of use are beyond our control. The manufacturers do not accept liability for any loss or damage, however arising, which results directly from the use of such information, nor do we offer any warranty of immunity against patent infringement.

**Typical Specifications****Daphne Oil Coat RL-55**

	<b>ASTM</b>	
	<b>METHOD</b>	
Colour	D-1500	L5.0
Density 15 °C g/cm <sup>3</sup>	D-4052	0.8255
Flash Point (COC) °C	D-93	98
Viscosity, cSt @ 40 °C	D-445	2.624
Pour Point, °C	D-6749	-37.5
Total Base Number (mgKOH/gm)	D-2896	1.04
Total Acid Number (mgKOH/gm)	D-974	0.84

The information provided is to our best knowledge, true & accurate, subjected to change without notification due to continual product research and development. All recommendations or suggestions are without guarantee since the conditions of use are beyond our control. The manufacturers do not accept liability for any loss or damage, however arising, which results directly from the use of such information, nor do we offer any warranty of immunity against patent infringement.